

# Acrylic Urethane RT-AU

## Product Description and Use

RT-AU is a two component, low viscosity acrylic urethane. It is used as a primer/ sealer over a variety of surfaces. The use of special solvents and adhesion promoters gives this material excellent penetration and adhesion to minimally profiled concrete. RT-AU is U.V. stable for use in exterior applications, cures rapidly and is easily re-coated with both solvent-based and water-based polyurethanes. When used as a finish coat, this material gives a hard, high gloss surface that offers excellent stain resistance and easy clean ability. Compared to solvent-based acrylic sealers, RT-AU offers substantial improvements in initial gloss, gloss retention and overall performance. RT-AU is available in a satin finish if a lower gloss is desired. A special version of this material is available to meet the 50 grams/liter VOC limit in California. RT-AU has been designed for use over concrete, acid-stained surfaces, and various types of architectural concrete. Its performance as a paver sealer is unexcelled. It is especially suitable over acid-stained concrete because it is unaffected by pH drifts that can affect the adhesion of other types of primers. When used over acid stains or integrally colored concrete, it gives color enhancement similar to solvent acrylic sealers. RT-AU can also be used as a tie coat over difficult to adhere to surfaces such as polyester urethane. When used as a finish coat in vehicle areas, it resists tire tracking and provides easy soil release. Although abrasion resistance to heavy foot traffic far exceeds single component materials, the best performance in these areas is achieved with polyester urethane's such as RT-CRU/UVR, RT-CRU VOC or RT-WBU.

## Chemical Composition

Acrylic oligomer cross linked with aliphatic isocyanate. System modified with U.V. absorbers, hindered amine light stabilizers and a proprietary adhesion promoter.

## Colors

Available in clear only.

## Limitations

- + Use over dense, minimally profiled surfaces requires machine scrubbing with a nylogrit type brush.
- + Do not use solvent acrylic as a primer for RT-AU
- + Applications heavier than 200 sq. ft. per gallon or puddling may result in solvent entrapment and possible blistering.
- + Do not use the satin material over an unprimed surface.

## WARRANTY INFORMATION

ResinTek Systems guarantees that this product is free from manufacturing defects and complies with our published specifications. In the event that the buyer proves that the goods received do not conform to these specifications or were defectively manufactured, the buyer's remedies shall be limited to either the return of the goods and repayment of the purchase price or replacement of the defective material at the option of the seller. ResinTek Systems MAKES NO OTHER WARRANTY, EXPRESSED OR IMPLIED, AND ALL WARRANTIES OF MERCHANT ABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE HEREBY DISCLAIMED. ResinTek Systems shall not be liable for damages caused by application of its products over concrete with excessive moisture vapor transmission or alkalinity. ResinTek Systems shall not be liable for any injury incurred in a slip and fall accident. Manufacturer or seller shall not be liable for prospective profits or consequential damages resulting from the use of this product.

# Acrylic Urethane RT-AU

## Technical Data

### Physical Properties

Mix Ratio	2:1
Solids Content	38%
Volatile Organic Compounds	400 grams/liter
Volatile Organic Compounds (California formulation)	38 grams/liter
Pot Life (77 degrees)	1 hour

### Cure Time (77 degrees)

Re-Coat	90 minutes
Light Traffic	4 hours
Vehicle Traffic	3 days

### Performance Properties

Gloss (60 degrees)	90
Hardness (Konig)	127
Flexibility	Passes 1/8 inch
Impact Resistance (ASTM D-2794)	Passes 3/8 inch-pounds direct impact
Tabor Abrasion (1000 gm. Load, 1000 cycles, CS 17 Wheel)	69 mg. loss
Adhesion to Concrete (ASTM 451)	Concrete fails before loss of bond

# Acrylic Urethane RT-AU

## Chemical and Stain Resistance (ASTM D-1308 24 Hour Immersion)

Coffee	
Vegetable Oil	No effect
Mustard	No effect
Whiskey	No effect
Urine	No effect
Gasoline	No effect
Motor Oil	No effect
Brake Fluid	No effect
Transmission Fluid	No effect
Skydrol	No effect
Mineral Spirits	No effect
10% Sulphuric Acid	No effect
10% Hydrochloric Acid	No effect
10% Acetic Acid	No effect
Xylene	Slight softening, film recovers
MEK	Film destroyed

# Acrylic Urethane RT-AU

## General Information

### Moisture Vapor Emissions Precautions

All interior concrete floors not poured over an effective moisture vapor retarder are subject to possible moisture vapor transmission that may lead to blistering and failure of the coating system. It is the coating applicator's responsibility to conduct calcium chloride and relative humidity probe testing to determine if excessive levels of vapor emissions are present before applying any coatings. RTS can supply moisture remediation products. Consult our technical service department. ResinTek Systems and its sales agents will not be responsible for coating failures due to undetected moisture vapor emissions.

### Surface Preparation

Although RT-AU has adhesion capabilities to challenging substrates, always profile the substrate as well as possible. Whenever possible acid-etch the surface using a floor machine with a nylogrit brush. Follow the printed RTS guidelines for surface preparation. If acid etching is not possible, clean the surface with a floor machine and nylogrit brush. Use RTS Orange Clean, 1 part to 8 parts water. Do not let detergent residue dry on the concrete. Rinse well. Acid-stained surfaces must be scrubbed with RTS Super Base Neutralizer, 8 oz. to 4 gallons of water. Rinse well and allow it to dry overnight.

### Mixing Instructions

Mix only that amount of product that can be used in a two- hour period at 77°F. Higher temperatures reduce pot life. The combining ratio is 2 parts A to 1 part B. Proportion the amounts carefully and mix for one full minute using a low-speed drill, scraping the bottom and sides of the mixing vessel. Avoid contamination with moisture. Reseal partially used containers completely after use.

### Application Recommendations

RT-AU may be applied by brush, roller, or airless sprayer. If rolling the material, use a ½ inch roller cover, work out of a 5-gallon pail or roller pan using the dip and roll method. Do not pour the material onto the floor. Because the material dries quickly, apply liberally, and work small areas. Application rate should be 200-300 sq. ft. per gallon. Do not over-apply or allow to puddle as solvent entrapment may occur. Do not use solvent acrylic sealers as a primer for this material.

### Recoating Guidelines

RT-AU has an indefinite recoat window when being recoated with itself. If recoating with Polyurethane 100 and more than 24 hours has elapsed, reduce the material with approximately 15% acetone (1 pint acetone to 1 gallon of mixed material). If recoating the RT-AU with Polyurethane 501 and more than 24 hours elapses, degloss the surface using a floor machine and a black janitor pad. Following these procedures will ensure good intercoat adhesion.

### Handling Precautions

Material is flammable. Extinguish all flames, pilot lights and electric motors until all vapors are gone and the coating is hard. The vapor is harmful. Use only with adequate ventilation or an appropriate cartridge type respirator. Avoid contact with skin, wear protective gloves. Read Material Safety Data Sheet before using it.

# Acrylic Urethane RT-AU

## Slip and Fall Precautions

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slip resistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. ResinTek Systems recommends the use of angular slip resistant aggregate in all coatings or flooring systems that may be exposed to wet, oily, or greasy conditions. It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. ResinTek Systems or its sales agents will not be responsible for injury incurred in a slip and fall accident.